

PRODUCT DATA SHEET

EVERBUILD® Gun Grade Expanding Foam

QUICK SETTING POLYURETHANE-BASED FOAM

PRODUCT DESCRIPTION

EVERBUILD® Gun Grade Expanding Foam is a quick setting polyurethane-based foam which expands greatly on application and yields up to 50 times the original can contents. Can be cut, sawn, plastered and sealed over after approximately one hour. Fills irregular gaps, fixes framework, insulates and sound deadens. Designed for professional use in conjunction with Gun Foam Applicators.

USES

Filling

- Gaps around pipe entries through walls.
- Gaps around window frames, door frames.
- Electrical wire chasing prior to plastering
- Deep joints prior to applying sealant or plaster
- Irregular gaps in stone, brick, concrete or plaster

Fixing

- Door frames
- Timber structures
- Window sills and thresholds.
- Window frames

Insulating

- Behind cladding to exterior walls.
- Behind soffit and barge boards

PRODUCT INFORMATION

Packaging	750 ml tin
Shelf Life	12 months in original containers at stated storage temperatures.
Storage Conditions	Store upright between 15 °C and 20 °C. Pressurized container. Protect from sunlight and do not expose to temperatures above 50 °C. Do not pierce or burn the can even after use. Store as flammable liquid. Note: Elevated temperatures will reduce shelf life dramatically.

TECHNICAL INFORMATION

CHARACTERISTICS / ADVANTAGES

- Quick setting - can be cut, sawn or plastered in 1 hour.
- Economical in use - expands up to 50 times its original volume.
- Fills irregular and broad gaps where most conventional fillers would fail.
- Possesses insulating and sound deadening properties.

Expansion	45 litres (750 ml can)
Cell Structure	Medium fine
Temp Res Of Cured Bead	Long Term: -40 to +80 °C Short Term: -40 to +100 °C

APPROVALS / STANDARDS

Building Material Class - B3

Compressive Strength	5 N/cm ² (DIN 53421) at 10 % stress.
Tensile Strength	18 N/cm ² (DIN 53455)
Elongation at Break	Elongation At Tension - 30 % (DIN 53455)
Shear Strength	8 N/cm ² (DIN 53422)
Dimensional Stability	Full Load Bearing Stability - App, 12 hours (20 mm bead)
Thermal Resistance	Thermal Conductivity - 0.04 W/Mk (DIN 52612)
Water Absorption	0.3 Vol % (DIN 53428)

APPLICATION INFORMATION

Ambient Air Temperature	5 °C - 25 °C. (Optimum 20 °C)
Cutting Time	20 mins to 1 hour depending on bead dimensions.
Tack Free Time	Approx. 8 minutes

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Ensure all surfaces are clean, sound and free from dust and loose particles. Moisten surfaces to be sealed with water. This assists the curing process.

APPLICATION METHOD / TOOLS

ALWAYS WEAR PROTECTIVE GLOVES.

Shake can well before use (about 20 times).

Carefully fix nozzle. Do not overtighten or force.

ALWAYS USE CAN UPSIDE DOWN. For EVERBUILD®

Gun Grade Expanding Foam, tighten securely into one of our range of guns.

Only partially fill cavities as the foam will expand to fill the remaining space. Any excess foam can be removed whilst still wet with EVERBUILD® FOAM CLEANER.

Cured foam must be removed mechanically. When used for fixing door frames, supports must be used until the foam is fully cured.

Please note:

When transported in cars, keep in boot, out of direct sunlight. When removing cured foam from skin, take care not to damage with abrasives. Grease skin with body lotion or similar.

IMPORTANT – Re-use is only possible by cleaning the nozzle and valve tip with EVERBUILD® FOAM CLEANER before the foam has cured. Do not push any object into the valve as the contents may explode.

LIMITATIONS

- Carefully read instructions and text in warning box before use.
- Do not over-pressurize container.
- Always apply above 5 °C.
- Clean spills immediately with EVERBUILD® FOAM CLEANER.
- When using EVERBUILD® Gun Grade Expanding Foam, always clean the gun thoroughly with EVERBUILD® FOAM CLEANER until the jet is clear of foam. Leave the canister attached until the gun is to be

used again

- When using, always remove nozzle from can and clean immediately after use with EVERBUILD® FOAM CLEANER
- For fire rated joints, use EVERBUILD® FIREFOAM B1 in conjunction with EVERBUILD® FIREMATE® intumescent sealant.
- Once cured, dry foam must be removed mechanically. No solvent will remove the product

VALUE BASE

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Consult MSDS for full list of hazards

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability

for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

EVERBUILD BUILDING PRODUCTS LTD

Site 41, Knowsthorpe Way
Cross Green Industrial Estate
Leeds, LS9 0SW
Tel: 0113 240 3456
Web: www.everbuild.co.uk
Twitter: @everbuild

SIKA LIMITED

Watchmead
Welwyn Garden City
Hertfordshire, AL7 1BQ
Tel: 01707 394444
Web: www.sika.co.uk
Twitter: @SikaLimited

SIKA IRELAND LIMITED

Ballymun Industrial Estate
Ballymun
Dublin 11, Ireland
Tel: +353 1 862 0709
Web: www.sika.ie
Twitter: @SikaIreland



Product Data Sheet

EVERBUILD® Gun
Grade Expanding
Foam
July 2020, Version
02.01
3/3 0600000000045



EVERBUILDGunGradeExpandingFoam-en-GBEVER-(07-2020)-2-1.pdf

BUILDING TRUST

